

# DIVERSIFIED

TESTING LABORATORIES, INC.

336 WEST FRONT STREET  
P.O. BOX 4004  
BURLINGTON, NORTH CAROLINA 27215  
Phone (336) 227-7710 • Fax (336) 227-1175

"We Test Per Your Request"

July 27, 2001

Reference: Laboratory Test Report  
Lab Identification No. 1438

Dear Mr. Propst:


One (1) fabric sample, identified as 100% POLYESTER POLY LINING; COLOR: EGGPLANT, was received and sprayed with "No Burn Fabric Gard" using 100% concentration and 100% wet pickup. The sample was then tested in accordance with the National Fire Protection Association No. 701, "Flame Resistant Textiles and Films, 1989 Edition, (Small Scale Test)". The results are as follows:

<u>Specimen Number</u>	<u>After Flame</u>		<u>Residual Flame</u>		<u>Char Length</u>	
	<u>Warp</u>	<u>Filling</u>	<u>Warp</u>	<u>Filling</u>	<u>Warp</u>	<u>Filling</u>
1	0.0	0.0	0.0	0.0	5.4	4.3
2	0.0	0.0	0.0	0.0	5.2	4.2
3	0.0	0.0	0.0	0.0	5.6	5.0
4	0.0	0.0	0.0	0.0	4.9	4.2
5	0.0	0.0	0.0	0.0	5.4	4.9
Avg.					4.9	

The fabric sample submitted meets the minimum requirements of the above standard. For fabrics whose weight does not exceed 6.0 oz./sq. yd., the average char length may not exceed 5.5 inches with no individual value exceeding 6.5 inches. Additionally, there may be no afterflame which exceeds 2.0 seconds and no residual flame on any of the specimens tested.

If there are any questions or when we can be of further assistance, please let us know.

Sincerely,



Karon S. Matkins

KSM/mr